Epoxy.com Product #459 Polyurethane Flexible Membrane

DESCRIPTION

Epoxy.com Product #459 is a two component, high solids, elastomeric urethane used in waterproofing applications. **Epoxy.com Product** #459 exhibits excellent elongation properties along with high tensile strength and tear resistance to make it an ideal crack resistant membrane for use under other Epoxy.com flooring systems. **Epoxy.com Product** #459 is also used with *Epoxy.com Elastomeric Systems*.

ADVANTAGES

- Bridges Hairline Cracks
- Resistant to Automotive Fluids
- Quick Cure Time
- One Coat Application
- Low Odor

Epoxy.com Product #459 is packaged with 41.5 pounds of Part A in a 6-gallon pail and 6 pounds of Part B in a gallon can to make a convenient 5-gallon unit.

CONSIDERATIONS

- Slabs on Grade Must Have an Efficient Vapor/Moisture Barrier
- Substrate Must be Free of Curing Agents and Other Foreign Materials\
- Minimum Application Temperature of 50°F
- Proper Respiratory Equipment Must Be Used When Required
- Do Not Apply Epoxy.com Product #459 to Wet or Damp Surfaces

TECHNICAL DATA

Color Grey

Mix Ratio by volume by weight 6.6 parts A - 1 part B 100 parts A - 13 parts B

Solids Content, by volume 96% Weight per Gallon, mixed 9.16 lbs

Pot Life 30 mins @ 77°F, 50% RH

Re-Coat Time 6 - 8 Hours

PERFORMANCE PROPERTIES

Tensile Strength ASTM-D-412 1500 psi Ultimate Elongation ASTM-D-412 350-400% Adhesion (unprimed) ASTM-D-904 60 pli Hardness Shore A ASTM-D-2240 70-80 Impact Resistance ASTM-D-2794 160 In. lb.

APPLICATION

SURFACE PREPARATION

Prepare surface in accordance with Epoxy.com Surface Preparation Guide New concrete must be cured at least 30 days. All concrete curing compound must be mechanically removed, along with any foreign material. Old concrete must be structurally sound and prepped according to guidelines.

PRIMING

Prime where necessary with Epoxy.com Product #899 Primer. Mix two (2) Parts A and one (1) Part B by volume with low speed drill for two minutes minimum. Apply with squeegee, brush, or roller. Do not puddle. Spread rate is approximately 250sq.ft./gallon.

INSTALLATION

Mix 6.6 Parts A to one (1) Part B by volume or 100 Parts A to 13 Parts B by weight using a low speed drill for 3 - 5 minutes. Epoxy.com Product #459 can be applied by using a roller, air brush, spray, or notched squeegee at a rate of 50 to 55 square feet per gallon to yield 28 to 30 dry mils.

CLEAN-UP

Clean tools with xylene or lacquer thinner.

FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

For more information please contact:

Epoxy.com.
352-489-1666 (Phone)
352-465-3497 (Fax)
info@epoxy.com
www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com 'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CO